

Foam-Control MAX[®] graphite enhanced molded polystyrene is for all types of industrial, packaging, and construction uses. Foam-Control MAX conforms to ASTM C578, “Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation”.

Foam-Control MAX is manufactured under an industry leading quality control program monitored by UL and further recognized in UL Evaluation Report UL ER11812-05.



| PRODUCT | |  | | | |
|--|--|--|---------------|---------------|---------------|
| | | 100 | 150 | 250 | |
| Compressive Strength ^{1,3} @ 10% deformation, min. ASTM D1621 | psi (kPa) | 10 (69) | 15 (104) | 25 (173) | |
| R-value ^{1,2} , Thermal Resistance, ASTM C518 | 40°F | °F·ft ² ·h/Btu (°K·m ² /W) | 5.2 (0.92) | 5.2 (0.92) | 5.3 (0.93) |
| | 75°F | °F·ft ² ·h/Btu (°K·m ² /W) | 5.0 (0.88) | 5.0 (0.88) | 5.0 (0.88) |
| Density, Nominal ASTM C303 | lb/ft ³ (kg/m ³) | 1.0 (16) | 1.5 (24) | 2.0 (32) | |
| Flexural Strength ¹ , min. ASTM C203 | psi (kPa) | 25 (173) | 35 (242) | 50 (345) | |
| Water Vapor Permeance ¹ of 1.0 in. thickness, max., perm ASTM E96 | | 5.0 | 3.5 | 2.5 | |
| Water Absorption ⁴ volume % ASTM C272 | | 0.3 | 0.3 | 0.3 | |
| Flame Spread ASTM E84 | | <25 | <25 | <25 | |
| Smoke Developed ASTM E84 | | <450 | <450 | <450 | |
| ASTM C578 Compliance, Type | | Type I | Type II | Type IX | |

¹ Please refer to ASTM C578 specification for complete information.

² R-values are based on 1-1/16" thickness.

³ Compressive strength is measured at 10 percent in accordance with ASTM C578.

A safety factor is required to prevent long-term creep for sustained loads. For static loads, a safety factor of 3:1 is recommended.

⁴ ASTM C272 24 hour immersion followed by 24 hour storage in 75°F/50%RH air.

Design Options.

Cost effective design is among the highest priorities for industrial, packaging, and construction applications. Foam-Control MAX products are available in a range of Types necessary to provide control of structural integrity, thermal resistance (R-value), and cost effectiveness.

Thermal Performance.

The R-value of Foam-Control MAX remains constant and does not suffer from R-value loss. The closed cell structure of Foam-Control MAX contains air and not blowing agents which deplete over time.

Powered by graphite®

Foam-Control MAX is comprised of many small pockets of air within a polymer matrix containing graphite. The graphite reflects radiant heat energy like a mirror, increasing the material's resistance to heat flow or R-value.

Exposure to Water and Water Vapor.

The mechanical properties of Foam-Control MAX are unaffected by moisture. Exposure to water or water vapor does not cause swelling.

Temperature Exposure/Flame Retardants.

Foam-Control MAX is able to withstand the rigors of temperature cycling, assuring long-term performance.

Although flame retardants used in the manufacture of Foam-Control MAX provide an important margin of safety, all EPS products must be considered combustible.

The maximum recommended long-term exposure temperature for Foam-Control MAX is 165°F (74°C).

Adhesives, Coatings, and Chemicals.

Solvents which attack Foam-Control MAX include esters, ketones, ethers, aromatic, and aliphatic hydrocarbons and their emulsions, among others. If Foam-Control MAX is to be placed in contact with materials (or their vapors) of unknown

composition, pretest for compatibility at maximum exposure temperature.

Do not install or use Foam-Control MAX with coal tar pitch, highly solvent-extended mastics, or solvent-based adhesives without adequate separation.

Proven to meet, or exceed, building codes.

Foam-Control is manufactured under an industry leading quality control program monitored by UL and further recognized in UL Evaluation Report UL ER11812-05. Foam-Control meets ASTM C578, "Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation".



Termite Resistant - Perform Guard®.

Foam plastic insulations have been shown to become termite infested under certain exposure conditions. Foam-Control MAX with Perform Guard® provides resistance to termite infestation.

Resistance to Mold and Mildew.

Foam-Control MAX will not decompose and will not support mold or mildew growth. Foam-Control MAX provides no nutrient value to plants or animals.

Product Protection.

Foam-Control MAX can be damaged by prolonged direct sunlight exposure or by reflected sunlight. Foam-Control MAX must be protected during storage, transportation, and at the project with a light colored opaque material. Please refer to the Foam-Control MAX Handling Instructions.

Warranty.

Foam-Control MAX Licensees offer a product warranty ensuring thermal performance, physical properties, and termite resistance.



**MOLDED
PRODUCTS**

A Division of Atlas Roofing Corporation

For further information contact us:

Phone: (800) 277-0967

www.atlasfoamcontrol.com



Foam-Control MAX products are manufactured by AFM Corporation licensees.

Copyright © 2020 AFM Corporation. All rights reserved. Printed in USA. Foam-Control MAX, Foam-Control MAX logo, Perform Guard, Powered by Graphite, and Next Generation Powered by Graphite are registered trademarks of AFM Corporation, Lakeville, MN.

UL logo is a registered trademark of UL LLC. USGBC logo is a registered trademark of U.S. Green Building Council.

FCM02-01/20



www.foam-control.com

**NEXT GENERATION
INSULATION POWERED
BY GRAPHITE®**